

**VELCRO EUROPE, S.A**

Ctra. Mataró a Granollers, km. 5,8  
08310 ARGENTONA (Barcelona) Spain  
Phone: (+34) 93 758 32 98 - Fax: (+34) 93 396 98 20  
infovesa@velcro.com / cs\_emea@velcro.com - http://www.velcro.com

**SHIP TO**

**PIXC'L Sarl**  
26-28 Rue du Chemin Vert  
78610 - LE PERRY EN YVELINES - FRANCE

**BILL TO**

**PIXC'L Sarl**  
26-28 Rue du Chemin Vert  
78610 - LE PERRY EN YVELINES - FRANCE

| CUSTOMER No. | TAX ID.       | SUPPLIER No. | SALES PERSON         | SERVICE CONTACT | E-MAIL             |
|--------------|---------------|--------------|----------------------|-----------------|--------------------|
| 197806       | FR49494025539 |              | Jacquemain, Emmanuel | Odile Taupin    | otaupin@velcro.com |
| DELIVERY     | ORDER NUMBER  | CUSTOMER PO  | TEST DATE            |                 |                    |
| 31229230     | 9051970       | 4322         | 12.07.2024           |                 |                    |

| DESCRIPTION                                                          | UoM | QTY. SHIPPED | BATCH NUMBER |
|----------------------------------------------------------------------|-----|--------------|--------------|
| VELCRO® Brand Loop FRT PS15 50mm BLACK 330 25 M<br>E01005033011525 / | M   | 125          | 7012855894   |

Material tested according federal aviation regulations 25853 (a) App. F, Part 1, (a) (1) (ii) (b) (1) (2) (3) (4) (8). CS 25.853 (a) appendix F1(A)(1) (amdt 27)

| CHARACTERISTIC                              | SPECIMEN N° |     |     | MEAN RESULT | SPECIFICATION<br>REQUIREMENT<br>(NOT EXCEEDING) | COMPLIANCE |
|---------------------------------------------|-------------|-----|-----|-------------|-------------------------------------------------|------------|
|                                             | 1           | 2   | 3   |             |                                                 |            |
| Burn Length mm.                             | 104         | 108 | 103 | 105         | 200                                             | PASS       |
| Combined after flame and glow time, seconds | 8           | 5   | 9   | 7           | 15                                              | PASS       |
| Flaming time of drips, seconds              | 0           | 0   | 0   | 0           | 5                                               | PASS       |

**Work Instruction 501-ANNEX-C**

The test has been done at tape width. Samples selected randomly of the order. The results only affect to the samples tested in this order.

This report is issued by electronic data processor and therefore carries no signature.

All documents managed by the software "GESDOC" are submitted to a controlled documentation system. Any printed copy should be considered immediately obsolete with the exception of the "controlled copy". The content of this document should be considered confidential and for internal use only. This report should be not reproduced partially without the written authorization of **VELCRO EUROPE, S.A**