26 rue du chemin vert 78610 Le Perray en Yvelines Tél. : 01 34 84 21 93

Mail: contact@by-pixcl.com



# Double sided adhesive tape GPT-020F

# **Product Data Sheet**

December 2019 Supersedes: October 2019

## **Product Description**

Double sided adhesive tape with polyester carrier Modified acrylic adhesive Film Liner

#### **Key Features**

- High adhesion to a variety of high and low surface energy substrate
- · High initial tack
- · All-purpose tape
- High shear and temperature resistance
- · Easy handling and converting due to polyester carrier
- Film Liner for clean handling and automatic unwinding activities

#### **Application ideas**

- Self-adhesive mounting of furniture trim, sealing profiles and cable ducts.
- Bonding and mounting of sales displays and billboards.
- Fixing of decorative trims and emblems.

## Construction

Adhesive	Modified Acrylic	
Adhesive side open face 1	0,095 mm	
Carrier	PET 0,012 mm, transparent	
Adhesive back side <sup>2</sup>	0,095 mm	
Total thickness without liner	0,202 mm	
Liner	Polypropylene film liner, white (0,100 ± 0,010 mm)	

<sup>&</sup>lt;sup>1</sup>The open face side is visible, when unwinding the roll.

Calipers are average values.

Calculation of the adhesive caliper based on an average density of 1.012 g/ cm<sup>3</sup>.

<sup>&</sup>lt;sup>2</sup> The back side is visible after removal of the liner.



26 rue du chemin vert 78610 Le Perray en Yvelines Tél. : 01 34 84 21 93

Mail: contact@by-pixcl.com

3M™ GPT-020F December 2019

# **Performance Characteristics**

Adhesion to Stainless Steel  acc. to Finat FTM1 (after 72 h at RT, angle: 180°,  Haul-off speed: 300 mm/min., (0,05 mm PET-Film)	11,30 N/cm
Adhesion to ABS  acc. to Finat FTM1 (after 72 h at RT, angle: 180°,  Haul-off speed: 300 mm/min., (0,05 mm PET-Film)	10,86 N/cm
Adhesion to Polycarbonate  acc. to Finat FTM1 (after 72 h at RT, angle: 180°,  Haul-off speed: 300 mm/min., (0,05 mm PET-Film)	12,32 N/cm
Adhesion to Polypropylene acc. to Finat FTM1 (after 72 h at RT, angle: 180 °, Haul-off speed: 300 mm/min., (0,05 mm PET-Film)	12,26 N/cm
Adhesion to Glass acc. to Finat FTM1 (after 72 h at RT, angle: 180°, Haul-off speed: 300 mm/min., (0,05 mm PET-Film)	11,79 N/cm
Static shear resistance to stainless steel acc. to Finat FTM8, 1 kg/ 1"x1", at RT	> 10.000 min
Static shear resistance to stainless steel acc. to Finat FTM8; 500 g /0.5"x1" at 90 °C	>10.000 min
Temperature Performance (SAFT, PSTC 17, 40 °C to 205 °C, 0.5 °C / min), 500 g / 1"x1"	> 190 °C
Temperature Performance (SAFT, PSTC 17, 40 °C to 205 °C, 0.5 °C / min), 1000 g / 1"x1"	> 160 °C



26 rue du chemin vert 78610 Le Perray en Yvelines Tél. : 01 34 84 21 93

Mail: contact@by-pixcl.com

3M™ GPT-020F December 2019

Storage & Shelf Life

Store at 16  $^{\circ}$ C=25  $^{\circ}$ C and 40-65  $^{\circ}$  relative humidity in its original box.

The product can be stored up to 18 months after date of manufacturing.

**Note:** The shelf life may be shortened if the original packaging is not properly sealed or stored in an environment with high temperatures or humidity

**Precautionary Information** 

For information please contact your local 3M Office.

www.3M.com

For Additional Information

To request additional product information or to arrange for sales

assistance, call......

Address correspondence to: 3M

**Important Notice** 

All statements, technical information and recommendations contained in this document are based upon tests or experience that 3M believes are reliable. However, many factors beyond 3M's control can affect the use and performance of a 3M product in a particular application, including the conditions under which the product is used and the time and environmental conditions in which the product is expected to perform. Since these factors are uniquely within the user's knowledge and control, it is essential that the user evaluate the 3M product to determine whether it is fit for a particular purpose and suitable for the user's method or application. All questions of liability relating to this product are governed by the terms of the sale subject, where applicable, to the prevailing law

Values presented have been determined by standard test methods and are average values not to be used for specification purposes. Our recommendations on the use of our products are based on tests believed to be reliable but we would ask that you conduct your own tests to determine their suitability for your applications. This is because 3M cannot accept any responsibility or liability direct or consequential for loss or damage caused as a result of our recommendations

3M is a trademark the 3M Company



3M Svenska AB Industri

Bollstanäsvägen 3 192 78 Sollentuna Tel: 08-92 21 00

www.3M.se/tejp

3M Norge AS Avd. Industri Tærudgata 16 2004 Lillestrøm Tlf.: 06384

www.3M.no/tape

3M a/s Industri

Hannemanns Allé 53 DK-2300 København S Tlf.: 43 48 01 00

www.3MIndustri.dk

Suomen 3M Oy Teollisuustuottett Keilaranta 6

02150 Espoo Puh: 09 525 21

www.3M.fi/teollisuus

Page 3 of 3